



---

**Research article**

**A guide to investigating colloidal nanoparticles by cryogenic transmission electron microscopy: pitfalls and benefits**

**Christophe A. Monnier<sup>1</sup>, David C. Th  venaz<sup>1</sup>, Sandor Balog<sup>1</sup>, Gina L. Fiore<sup>1</sup>,  
Dimitri Vanhecke<sup>1</sup>, Barbara Rothen-Rutishauser<sup>1</sup>, and Alke Petri-Fink<sup>1,2,\*</sup>**

<sup>1</sup> Adolphe Merkle Institute, University of Fribourg, Chemin des Verdiers 4, 1700 Fribourg, Switzerland

<sup>2</sup> Chemistry Department, University of Fribourg, Chemin du Mus   9, 1700 Fribourg, Switzerland

\* **Correspondence:** Email: [alke.fink@unifr.ch](mailto:alke.fink@unifr.ch).

**Supplementary information**

**Dynamic light scattering—Calculations**

The field auto-correlation function  $g_1(t)$  from uniform particles follows a negative exponential trend as a function of time (R. Pecora, *Dynamic Light Scattering: Applications of Photon Correlation Spectroscopy*, Plenum Press, New York, 1985):

$$g_1(t) = e^{-\Gamma_T t}, \quad (1)$$

where  $\Gamma_T$  is the relaxation time corresponding to translational Brownian motion of the suspended particle. The relaxation time is a function of particle size:

$$\Gamma_T = q^2 \frac{k_B T}{6\pi\eta R}, \quad (2)$$

where  $R$  is the hydrodynamic radius,  $k_B$  the Boltzmann constant,  $T$  the temperature,  $\eta$  the viscosity of the solvent,  $q$  the momentum transfer  $q = \frac{4\pi}{\lambda} n \sin\left(\frac{\theta}{2}\right)$ ,  $\theta$  the scattering angle,  $\lambda$  the wavelength of the laser, and  $n$  the refractive index of the solution. Equation 1 can be extended for polydisperse particles, by considering that in a given sample each particle contributes to the scattering intensity, depending on its size. The intensity-weighted correlation function then can be approximated as


$$g_1(t) \cong \frac{\sum_{j=1}^N V_j^2 g_{1j}(t)}{\sum_{j=1}^N V_j^2} \quad (3)$$

where

$$V_j = \frac{4\pi}{3} R_j^3 \quad (4)$$

is the volume of the  $j^{\text{th}}$  particle, and  $g_{1j}(t)$  the correlation function (Equation 1) corresponding to the size of this particle (Equation 2), and  $N$  is the number of counted particles.

### Ice—a common artefact found in cryo-TEM



**Suppl. Figure 1. Ice contaminants are constant acquaintances in cryo-TEM. Depending on the sample mounting procedure or the surroundings (*e.g.* humidity), water can freeze on the vitreous layer. Some classic appearances are shown in A/B. Ethane contamination from the plunge-freezing process may also be found (B, upper left).**